
Concave Grating

Rowland Circle Mounting






Grating specification

Groove density	2700 ± 4 l/mm
Groove profile	Sinusoidal
Diffraction grating area	≥ Ø 35 mm
Reflective coating	Aluminum (unprotected)
Grating master type	Holographically recorded
Grating type	Epoxy replica (copy)
Storage and transport temperature	-40 °C +70 °C (non-condensing environment)

Mounting specification (Schematic drawing)




By historic convention clockwise incident and diffraction angles are positive.


Optical grating characteristics

Diffraction efficiency (unpolarized @ cAD = 32°)

200 nm	≥ 30 %	
265 nm	≥ 34 %	
350 nm	≥ 32 %	

Typical relative diffraction efficiency (rDE) in first diffraction order






Typical efficiency curves based on rigorous electromagnetic modeling using measured AFM profiles. rDE refers to the ratio between diffracted power from the grating and reflected power from a mirror coated with the same material.






Blank specification

Material	Zerodur (extremely low expansion glass ceramic)	
Radius of curvature	501.19 mm	
Protective bevel (left surface)	0.5 mm	





Carl Zeiss Spectroscopy GmbH 07740 Jena Germany

 Phone:
 + 49 (0) 3641 64-2838

 Fax:
 + 49 (0) 3641 64-2485

 E-mail:
 info.spectroscopy@zeiss.com

 Internet:
 www.zeiss.com/spectroscopy

